

EST 1945

ODIN

MAURICE KAIN

DESIGNED IN NEW ZEALAND & AUSTRALIA
MADE ACROSS THE GLOBE

mk
Maurice Kain








Maurice Kain

ODIN with weighted base


FR WIDE WIDTH SHEER
DRAPERY FABRIC



COLLECTION NAME	ODIN	PATTERN REPEAT	Nil
DESIGN NAME	ODIN	CONTINUOUS	N
BRAND	MAURICE KAIN	ADDITIONAL FINISHING	Base Weight
NUMBER OF COLOURS	15	WEIGHT (GSM)	148gsm
FABRIC TYPE	SHEER	ROLL SIZE	40m
USAGE	CURTAINS	COLOURFASTNESS TO LIGHT	5
COMPOSITION	100% POLYESTER	FLAMMABILITY	AS/NZS 1530.2 & 1530.3
WIDTH	320cm	ABRASION	N/A

CARE INSTRUCTIONS

Regular care will minimize need for additional cleaning. Gently vacuum with appropriate attachment. Always exercise caution when spot cleaning. Test clean on non-exposed surface. Remove hooks rings & trims before cleaning. Gently vacuum regularly with appropriate attachment. Warm hand wash. Do not bleach. Do not rub or wring. Drip dry in shade. For best results hang curtains by their hooks to damp dry immediately. Use warm iron. Dry cleanable P 50. Possible shrinkage 3%.



AVAILABLE COLOURS




ALABASTER




ASH



BIRCH



EBONY



GRANITE



LINEN



MARBLE



MINK



NATURAL



PARCHMENT



PORCELAIN




QUARRY



SHADOW



STORM



WHITE

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Basford Brands Pty Ltd
16 - 20 Apparel Close
Breakwater VIC 3219

Test Number : 16-005954
Issue Date : 30/11/2016
Print Date : 30/11/2016

Sample Description Clients Ref : "ODIN"
Polyester Sheer with weighted base
Colour : Alabaster
End Use : Drapery
Nominal Composition : 100% Polyester
Nominal Mass per Unit Area/Density : 148g/m²
Nominal Thickness : Approx: 0.5mm

AS/NZS 1530.3-1999

Methods for Fire Tests on Building Materials, Components and Structures Part 3: Simultaneous Determination of Ignitability, Flame Propagation, Heat Release and Smoke Release

Face tested:	Face		
Date tested:	30/11/2016		
	Standard Error	Mean	
Ignition time	Nil	Nil	min
Flame propagation time	Nil	Nil	sec
Heat release integral	Nil	Nil	kJ/m ²
Smoke release, log d	0.0440	-1.8228	
Optical density, d		0.0155	/ metre

Number of specimens ignited:	0
Number of specimens tested:	6

Regulatory Indices:	
Ignitability Index	0 Range 0-20
Spread of Flame Index	0 Range 0-10
Heat Evolved Index	0 Range 0-10
Smoke Developed Index	1 Range 0-10

77583

16017

Page 1 of 3

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025

- Chemical Testing
- Mechanical Testing
- Performance & Approvals Testing

: Accreditation No. 983
: Accreditation No. 985
: Accreditation No. 1356



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc. (Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Basford Brands Pty Ltd
16 - 20 Apparel Close
Breakwater VIC 3219

Test Number : 16-005954
Issue Date : 30/11/2016
Print Date : 30/11/2016

These results only apply to the specimen mounted, as described in this report. The result of this fire test may be used to directly assess fire hazard, but it should be recognised that a single test method will not provide a full assessment of fire hazard under all fire conditions.

Ignition is initiated by a pilot flame that is held near, but does not touch the specimen. A material that does not ignite during the standard test may ignite if contacted with a pilot flame during the test

The specimens melted and flowed away from the area of maximum heat during the test. Due to this phenomena it should be recognised that this test result may not be a true indication of the product's fire hazard properties.

The specimens were mounted to simulate use in an unsupported or free hanging mode. The results may be significantly different when mounted to simulate a wall cladding or upholstery application.

To allow free movement of sample during testing all corners were folded away from the clamps.

Each test specimen was sandwiched between two layers of galvanised welded square mesh made from wire of nominal diameter 0.8mm and nominal spacing 12mm in both directions, stapled through at four points, each 100mm from the centre of the sample and the assembly clamped in four places.

77583

16017

Page 2 of 3

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025

- Chemical Testing
- Mechanical Testing
- Performance & Approvals Testing

: Accreditation No. 983
: Accreditation No. 985
: Accreditation No. 1356



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

0204/11/06

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc. (Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Basford Brands Pty Ltd
16 - 20 Apparel Close
Breakwater VIC 3219

Test Number : 16-005954
Issue Date : 30/11/2016
Print Date : 30/11/2016

AS 1530.2-1993

Methods for Fire Tests on Building Materials, Components and Structures. Part 2: Test for Flammability of Materials

Date Tested	22/11/2016	
Flammability Index	2	
	Length	Width
Spread Factor	1	1
Heat Factor	1	1
Maximum height (d)		
Mean	3.5	3.3
Coefficient of Variation	0.0	8.4 %
Heat (a)		
Mean	1.5	1.5 °C.min
Coefficient of Variation	0.0	0.0 %
Number of Specimens Tested	6	6
Observation	Visible smoke, melting dripping flaming debris	

These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test, and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use.

77583

16017

Page 3 of 3

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025
- Chemical Testing
- Mechanical Testing
- Performance & Approvals Testing

: Accreditation No. 983
: Accreditation No. 985
: Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



0204/11/06

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR