

EST 1945

AUDIBLE & PHONIC ACOUSTIC

MAURICE KAIN

DESIGNED IN NEW ZEALAND & AUSTRALIA
MADE ACROSS THE GLOBE

mk
Maurice Kain


ACOUSTIC



Maurice Kain

AUDIBLE & PHONIC


ACOUSTIC TRIPLE WEAVE FIRE RETARDANT
TEXTURED PLAIN DRAPERY FABRIC




COLLECTION NAME	Audible & Phonic	PATTERN REPEAT	Nil
DESIGN NAME	Audible & Phonic	CONTINUOUS	N
BRAND	MAURICE KAIN	ADDITIONAL FINISHING	/
NUMBER OF COLOURS	10	WEIGHT (GSM)	280gsm
FABRIC TYPE	PLAIN	ROLL SIZE	Audible 27m/Phonic 40m
USAGE	CURTAINS	COLOURFASTNESS TO LIGHT	6
COMPOSITION	100% POLYESTER	FLAMMABILITY	AS/NZS 1530.2 & 1530.3
WIDTH	320cm/160cm	ABRASION	N/A

CARE INSTRUCTIONS


Regular care will minimize need for additional cleaning. Gently vacuum with appropriate attachment. Always exercise caution when spot cleaning. Test clean on non-exposed surface. Remove hooks rings and trims before cleaning. Do not soak, rub or wring. Drip dry in shade. Possible shrinkage 3%



AVAILABLE COLOURS




ASH




CARBON



CHARCOAL




LINEN




NATURAL




NUTMEG




SHELL



SLATE



STONE



WOODLANDS

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Basford Brands Pty Ltd
16 - 20 Apparel Close
Breakwater VIC 3219

Test Number : 19-006117
Issue Date : 4/11/2019
Print Date : 4/11/2019

Sample Description Clients Ref : "Audible & Phonic"
Woven curtain fabric Colour : Stone
Nominal Composition :
100% Polyester
Nominal Mass per Unit Area/Density : 280g/m2

AS 1530.2-1993

Methods for Fire Tests on Building Materials, Components and Structures. Part 2: Test for Flammability of Materials

Date Tested	04/11/2019	
Flammability Index	6	
	Length	Width
Spread Factor	0	5
Heat Factor	1	1
Maximum height (d)		
Mean	1.7	5.1
Coefficient of Variation	15.5	32.0 %
Heat (a)		
Mean	1.5	4.0 °C.min
Coefficient of Variation	0.0	77.8 %
Number of Specimens Tested	6	9
Observation	Melting, visible smoke	

These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test, and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use.

184733

39909

Page 1 of 1

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing
- Mechanical Testing
- Performance & Approvals Testing

: Accreditation No. 983
: Accreditation No. 985
: Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



0204/11/06

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc. (Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Basford Brands Pty Ltd
16 - 20 Apparel Close
Breakwater VIC 3219

Test Number : 19-006118
Issue Date : 11/11/2019
Print Date : 11/11/2019

Sample Description Clients Ref : "Audible & Phonic"
Woven curtain fabric Colour : Stone
Nominal Composition :
100% Polyester
Nominal Mass per Unit Area/Density : 280g/m²
Nominal Thickness : Approx 1mm

AS/NZS 1530.3-1999

Methods for Fire Tests on Building Materials, Components and Structures Part 3: Simultaneous Determination of Ignitability, Flame Propagation, Heat Release and Smoke Release

Face tested:	Face		
Date tested:	11/11/2019		
	Standard Error		Mean
Ignition time	Nil		Nil min
Flame propagation time	Nil		Nil sec
Heat release integral	Nil		Nil kJ/m ²
Smoke release, log d	0.1415		-1.5722
Optical density, d			0.0323 / metre
Number of specimens ignited:			0
Number of specimens tested:			6
Regulatory Indices:			
Ignitability Index			0 Range 0-20
Spread of Flame Index			0 Range 0-10
Heat Evolved Index			0 Range 0-10
Smoke Developed Index			2 Range 0-10

185139

39910

Page 1 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing
- Mechanical Testing
- Performance & Approvals Testing

: Accreditation No. 983
: Accreditation No. 985
: Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc. (Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Basford Brands Pty Ltd
16 - 20 Apparel Close
Breakwater VIC 3219

Test Number : 19-006118
Issue Date : 11/11/2019
Print Date : 11/11/2019

The reaction of thin unsupported flexible materials to flame impingement can be assessed in accordance with AS 1530.2. Where materials of thickness less than 2mm that are sufficiently flexible to be bent by hand around a mandrel of 2mm diameter or less are subjected to the test described herein, they should also be subjected to the test in AS 1530.2.

Ignition is initiated by a pilot flame that is held near, but does not touch the specimen. A material that does not ignite during the standard test may ignite if contacted with a pilot flame during the test.

The specimens melted and flowed away from the area of maximum heat during the test. Due to this phenomena it should be recognised that this test result may not be a true indication of the product's fire hazard properties.

The specimens were mounted to simulate use in an unsupported or free hanging mode. The results may be significantly different when mounted to simulate a wall cladding or upholstery application.

To allow free movement of sample during testing all corners were folded away from the clamps.

Each test specimen was sandwiched between two layers of galvanised welded square mesh made from wire of nominal diameter 0.8mm and nominal spacing 12mm in both directions, stapled through at four points, each 100mm from the centre of the sample and the assembly clamped in four places.

These results only apply to the specimen mounted, as described in this report. The result of this fire test may be used to directly assess fire hazard, but it should be recognised that a single test method will not provide a full assessment of fire hazard under all fire conditions.

185139

39910

Page 2 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing
- Mechanical Testing
- Performance & Approvals Testing

: Accreditation No. 983
: Accreditation No. 985
: Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc. (Hons)
MANAGING DIRECTOR