

EST 1945

INTAGLIO

# MAURICE KAIN

DESIGNED IN NEW ZEALAND & AUSTRALIA  
MADE ACROSS THE GLOBE

*mk*  
Maurice Kain








Maurice Kain

# INTAGLIO with weighted base


FR WIDE WIDTH SHEER  
DRAPERY FABRIC



<b>COLLECTION NAME</b>	Intaglio	<b>PATTERN REPEAT</b>	Nil
<b>DESIGN NAME</b>	Intaglio	<b>CONTINUOUS</b>	Y
<b>BRAND</b>	Maurice Kain	<b>ADDITIONAL FINISHING</b>	Weighted Base
<b>NUMBER OF COLOURS</b>	11	<b>WEIGHT (GSM)</b>	136gsm
<b>FABRIC TYPE</b>	Plain	<b>ROLL SIZE</b>	40m
<b>USAGE</b>	Sheer	<b>COLOURFASTNESS TO LIGHT</b>	6
<b>COMPOSITION</b>	100% POLYESTER	<b>FLAMMABILITY</b>	AS/NZS 1530.2 & 1530.3
<b>WIDTH</b>	298cm	<b>ABRASION</b>	N/A

## CARE INSTRUCTIONS

Regular care will minimize need for additional cleaning. Gently vacuum with appropriate attachment. Always exercise caution when spot cleaning. Test clean on non-exposed surface. Remove hooks rings & trims before cleaning. Gently vacuum regularly with appropriate attachment. Warm hand wash. Do not bleach. Do not rub or wring. Drip dry in shade. For best results hang curtains by their hooks to damp dry immediately. Use warm iron. Dry cleanable P 50. Possible shrinkage 3%.



## AVAILABLE COLOURS



ALABASTER



ASH



BLACK



CHARCOAL



CLOUD



FLINT



IVORY




LINEN



MIST



SKY



WHITE

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT

**Client :** Basford Brands Pty Ltd  
16 - 20 Apparel Close  
Breakwater VIC 3219

**Test Number :** 17-003133  
**Issue Date :** 28/06/2017  
**Print Date :** 28/06/2017

**Sample Description** Clients Ref : "Intaglio"  
Decorative Polyester Sheer Fabric  
End Use : Drapery  
Nominal Composition : Polyester  
Nominal Mass per Unit Area/Density : 136g/m2

AS 1530.2-1993

### Methods for Fire Tests on Building Materials, Components and Structures. Part 2: Test for Flammability of Materials

Date Tested	27/06/2017	
Flammability Index	5	
	Length	Width
Spread Factor	4	2
Heat Factor	1	1
Maximum height (d)		
Mean	4.7	4.0
Coefficient of Variation	11.1	0.0 %
Heat (a)		
Mean	1.5	1.5 °C.min
Coefficient of Variation	0.0	0.0 %
Number of Specimens Tested	6	6
Observation	Visible smoke, melting dripping flaming debris.	

These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test, and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use.

96094

20227

Page 1 of 1

© Australian Wool testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025

- Chemical Testing  
- Mechanical Testing  
- Performance & Approvals Testing

: Accreditation No. 983  
: Accreditation No. 985  
: Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



0204/11/06

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc. (Hons)  
MANAGING DIRECTOR

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT

**Client :** Basford Brands Pty Ltd  
16 - 20 Apparel Close  
Breakwater VIC 3219

**Test Number :** 17-003132  
**Issue Date :** 27/06/2017  
**Print Date :** 27/06/2017

**Sample Description** Clients Ref : "Intaglio"  
Decorative Polyester Sheer Fabric  
End Use : Drapery  
Nominal Composition : Polyester  
Nominal Mass per Unit Area/Density : 136g/m2

AS/NZS 1530.3-1999

### Methods for Fire Tests on Building Materials, Components and Structures Part 3: Simultaneous Determination of Ignitability, Flame Propagation, Heat Release and Smoke Release

Face tested:	Face		
Date tested:	26/06/2017		
	Standard Error		Mean
Ignition time	Nil		Nil min
Flame propagation time	Nil		Nil sec
Heat release integral	Nil		Nil kJ/m <sup>2</sup>
Smoke release, log d	0.0505		-1.7731
Optical density, d			0.0174 / metre
Number of specimens ignited:			0
Number of specimens tested:			6
Regulatory Indices:			
Ignitability Index			0 Range 0-20
Spread of Flame Index			0 Range 0-10
Heat Evolved Index			0 Range 0-10
Smoke Developed Index			2 Range 0-10

96007

20226

Page 1 of 2

© Australian Wool testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025

- Chemical Testing  
- Mechanical Testing  
- Performance & Approvals Testing

: Accreditation No. 983  
: Accreditation No. 985  
: Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



0204/11/06

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc. (Hons)  
MANAGING DIRECTOR

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT

**Client :** Basford Brands Pty Ltd  
16 - 20 Apparel Close  
Breakwater VIC 3219

**Test Number :** 17-003132  
**Issue Date :** 27/06/2017  
**Print Date :** 27/06/2017

These results only apply to the specimen mounted, as described in this report. The result of this fire test may be used to directly assess fire hazard, but it should be recognised that a single test method will not provide a full assessment of fire hazard under all fire conditions.

The reaction of thin unsupported flexible materials to flame impingement can be assessed in accordance with AS 1530.2. Where materials of thickness less than 2mm that are sufficiently flexible to be bent by hand around a mandrel of 2mm diameter or less are subjected to the test described herein, they should also be subjected to the test in AS 1530.2.

Ignition is initiated by a pilot flame that is held near, but does not touch the specimen. A material that does not ignite during the standard test may ignite if contacted with a pilot flame during the test.

The specimens were mounted to simulate use in an unsupported or free hanging mode. The results may be significantly different when mounted to simulate a wall cladding or upholstery application.

To allow free movement of sample during testing all corners were folded away from the clamps.

Each test specimen was sandwiched between two layers of galvanised welded square mesh made from wire of nominal diameter 0.8mm and nominal spacing 12mm in both directions, stapled through at four points, each 100mm from the centre of the sample and the assembly clamped in four places.

96007

20226

Page 2 of 2

© Australian Wool testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025

- Chemical Testing  
- Mechanical Testing  
- Performance & Approvals Testing

: Accreditation No. 983  
: Accreditation No. 985  
: Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



0204/11/06

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR