
filigree COMPLETE LIVING

MARTINIQUE WITH BASE WEIGHT

FR WIDE WIDTH SHEER DRAPERY FABRIC

COLLECTION NAME **DESIGN NAME** BRAND NUMBER OF COLOURS **FABRIC TYPE** USAGE COMPOSITION WIDTH

Martinique Martinique Filigree 11 Plain Sheer 100% Polyester 320cm



PATTERN REPEAT

ADDITIONAL FINISHING

warm iron on

fabric side only do not tumble dry

CONTINUOUS

WEIGHT (GSM)

FLAMMABILITY

ROLL SIZE

ABRASION

warm hand wash





Nil Υ Weighted base 80gsm 40m **COLOURFASTNESS TO LIGHT** 6 AS/NZS 1530.2 & 1530.3 N/A

do not bleach dryclean P50

CARE INSTRUCTIONS

Regular care will minimize need for additional cleaning. Gently vacuum with appropriate attachment. Always exercise cation when spot cleaning. Test clean on nonexposed surface. Remove hooks rings & trims before cleaning. Gently vacuum regularly with appropriate attachment. Warm hand wash. Do not bleach. Do not rub or wring. Drip dry in shade. For best results hang curtains by their hooks to damp dry immediately. Use warm iron. Dry cleanable P 50. Possible shrinkage 3%.

AVAILARIE COLOURS

AVAILABLE COLOURS							
ASH	BLACKJACK	CHARCOAL	DUSK	HAZE			
ICE	LINEN	MERINO	SILVER	SNOW			







Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Basford Brands Pty Ltd 16 - 20 Apparel Close Breakwater VIC 3219		Test Number Issue Date Print Date	: 19-00185 : 11/04/201 : 11/04/201	19
Sample Description	Clients Ref : Martinique/Galway Sheer woven curtain fabric Colour : Silver End Use : Curtains Nominal Composition : 100% Polyester Nominal Mass per Unit Area/Density : ⁸⁰ g. Nominal Thickness : Approximately 1mm	/m2		
AS/NZS 1530.3-1999	Methods for Fire Tests on Building Materials, (Part 3: Simultaneous Determination of Ignitab Flame Propagation, Heat Release and Smoke I	ility,	Ires	
	Face tested:	Face		
	Date tested:	10/04/2019		
		Standard Error	Mean	
	Ignition time	Nil	Nil	min
	Flame propagation time	Nil	Nil	sec
	Heat release integral	Nil	Nil	kJ/m²
	Smoke release, log d	0.0406	-1.6574	
	Optical density, d		0.0225	/ metre
	Number of specimens ignited:		0	
	Number of specimens ignited: Number of specimens tested:		0 6	
	Number of specimens tested: Regulatory Indices:		6	Bango 0.20
	Number of specimens tested: Regulatory Indices: Ignitability Index		6	Range 0-20 Range 0-10
	Number of specimens tested: Regulatory Indices:		6	Range 0-20 Range 0-10 Range 0-10

162530

35267

© Australian Wool testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing - Mechanical Testing - Performance & Approvals Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

: Accreditation No. : Accreditation No. : Accreditation No.

983 985 1356 AWTĂ

Page 1 of 2



Allowed d.

APPROVED SIGNATORY



Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Basford Brands Pty Ltd 16 - 20 Apparel Close Breakwater VIC 3219

 Test Number
 :
 19-001855

 Issue Date
 :
 11/04/2019

 Print Date
 :
 11/04/2019

These results only apply to the specimen mounted, as described in this report. The result of this fire test may be used to directly assess fire hazard, but it should be recognised that a single test method will not provide a full assessment of fire hazard under all fire conditions.

The reaction of thin unsupported flexible materials to flame impingement can be assessed in accordance with AS 1530.2. Where materials of thickness less than 2mm that are sufficiently flexible to be bent by hand around a mandrel of 2mm diameter or less are subjected to the test described herein, they should also be subjected to the test in AS 1530.2.

Ignition is initiated by a pilot flame that is held near, but does not touch the specimen. A material that does not ignite during the standard test may ignite if contacted with a pilot flame during the test.

The specimens were mounted to simulate use in an unsupported or free hanging mode. The results may be significantly different when mounted to simulate a wall cladding or upholstery application.

To allow free movement of sample during testing all corners were folded away from the clamps.

Each test specimen was sandwiched between two layers of galvanised welded square mesh made from wire of nominal diameter 0.8mm and nominal spacing 12mm in both directions, stapled through at four points, each 100mm from the centre of the sample and the assembly clamped in four places.

162530

Australian Wool testing Authority Ltd Copyright - All Rights Reserved

35267



the Managing Director of AWTA Ltd.

Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing - Mechanical Testing - Performance & Approvals Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by

: Accreditation No. : Accreditation No. : Accreditation No.

on No. 983 on No. 985 on No. 1356 5

Page 2 of 2



MICHAEL A. JACKSON B.Sc.(Hons)

APPROVED SIGNATORY

C