AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT

Client: Basford Brands Pty Ltd

16 - 20 Apparel Close Breakwater VIC 3219 **Test Number** : 22-005072

Issue Date : 21/12/2022 Print Date : 21/12/2022

Sample Description Clients Ref: "Aruba"

Sheer woven fabric Colour : White End Use : Curtains

Nominal Composition:

100% Polyester

Nominal Mass per Unit Area/Density: 95g/m2



286098 62184 Page 1 of 2

Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



APPROVED SIGNATORY



MICHAEL A. JACKSON B.Sc.(Hons)

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT

Client: Basford Brands Pty Ltd Test Number: 22-005072

 16 - 20 Apparel Close
 Issue Date
 : 21/12/2022

 Breakwater VIC 3219
 Print Date
 : 21/12/2022

AS 1530.2-1993

Methods for Fire Tests on Building Materials, Components and Structures.

Part 2: Test for Flammability of Materials

Date Tested		21-12-2022	
Flammability Index		1	
	Length	Width	
Spread Factor	0	0	
Heat Factor	1	1	
Maximum height (d)			
Mean	1.0	1.0	
Coefficient of Variation	0.0	0.0	%
Heat (a)			
Mean	1.5	1.5	°C.min
Coefficient of Variation	0.0	0.0	%
Neural and Considering Total	_	_	
Number of Specimens Tested	6	6	

Observation Melting.

These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test, and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use.

286098 62184 Page 2 of 2

Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



MICHAEL A. JACKSON B.Sc.(Hons)

Chris Campbell

APPROVED SIGNATORY