

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

	IESI REPO	RI		
Client : Basford Bra	nds Pty Ltd	Test Number	: 18-00400	4
16 - 20 Apparel Close		Issue Date	: 2/08/2018	3
Breakwater	VIC 3219	Print Date	: 2/08/2018	3
Sample Description	Clients Ref : "Resene Origin"			
	Plain woven acrylic coated blind fabric			
	Colour : Grey End Use : Blinds			
	End Use : Blinds Nominal Composition : 100% Polyester			
	•	365g/m2		
NZS 1530.3-1999	Methods for Fire Tests on Building Materia Part 3: Simultaneous Determination of Igni Flame Propagation, Heat Release and Smo	tability,	res	
	Face tested:	Face		
	Date tested:	02/08/2018		
		Standard Error	Mean	
	Ignition time	0.36	7.08	min
	Flame propagation time	1.9	18.6	sec
	Heat release integral	2.3	91.8	kJ/m²
	Smoke release, log d	0.0114	-0.5257	
	omore release, log a	0.0114	-0.5257	
	Optical density, d	0.0114		/ metre
		0.0114		/ metre
	Optical density, d	0.0114	0.2989	/ metre
	Optical density, d Number of specimens ignited: Number of specimens tested: Regulatory Indices:	0.0114	0.2989 9	
	Optical density, d Number of specimens ignited: Number of specimens tested: Regulatory Indices: Ignitability Index		0.2989 9 9 13	Range 0-2
	Optical density, d Number of specimens ignited: Number of specimens tested: Regulatory Indices: Ignitability Index Spread of Flame Index		0.2989 9 9	Range 0-2 Range 0-1
	Optical density, d Number of specimens ignited: Number of specimens tested: Regulatory Indices: Ignitability Index		0.2989 9 9 13	

137862

29243

© Australian Wool testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing - Mechanical Testing - Performance & Approvals Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

: Accreditation No. : Accreditation No. : Accreditation No.

983 985 1356



Page 1 of 2



APPROVED SIGNATORY

12



Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Basford Brands Pty Ltd 16 - 20 Apparel Close Breakwater VIC 3219

18-004004 Test Number : **Issue Date** 2/08/2018 2/08/2018 **Print Date** •

These results only apply to the specimen mounted, as described in this report. The result of this fire test may be used to directly assess fire hazard, but it should be recognised that a single test method will not provide a full assessment of fire hazard under all fire conditions.

The reaction of thin unsupported flexible materials to flame impingement can be assessed in accordance with AS 1530.2. Where materials of thickness less than 2mm that are sufficiently flexible to be bent by hand around a mandrel of 2mm diameter or less are subjected to the test described herein, they should also be subjected to the test in AS 1530.2.

The specimens were mounted to simulate use in an unsupported or free hanging mode. The results may be significantly different when mounted to simulate a wall cladding or upholstery application .

To allow free movement of sample during testing all corners were folded away from the clamps.

Each test specimen was sandwiched between two layers of galvanised welded square mesh made from wire of nominal diameter 0.8mm and nominal spacing 12mm in both directions, stapled through at four points, each 100mm from the centre of the sample and the assembly clamped in four places.

137862

Australian Wool testing Authority Ltd Copyright - All Rights Reserved

29243



the Managing Director of AWTA Ltd.

Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing Mechanical Testing Performance & Approvals Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd

: Accreditation No Accreditation No · Accreditation No

1356

983 985

Page 2 of 2





C