## **AWTA Product Testing**

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

## **TEST REPORT**

Client: Basford Brands Pty Ltd

> 16 - 20 Apparel Close Breakwater VIC 3219

18-003768 Test Number : **Issue Date** 

17/07/2018

1/000

**Print Date** 17/07/2018

Weylands **Sample Description** Clients Ref:

> Linen look plain fabric Green Colour: End Use: Curtains

100% Polyester Nominal Composition:

380g/m2 Nominal Mass per Unit Area/Density:

AS/NZS 1530.3-1999

Methods for Fire Tests on Building Materials, Components and Structures Part 3: Simultaneous Determination of Ignitability, Flame Propagation, Heat Release and Smoke Release

Face tested: Face

Date tested: 17/07/2018

	Standard Error	wean	
Ignition time	0.98	5.17	min
Flame propagation time	Nil	Nil	sec
Heat release integral	7.1	30.6	kJ/m²
Smoke release, log d	0.1513	-0.8081	

04----

Optical density, d 0.2027 / metre

No of samples which ignited 8

For Samples which ignited

Smoke Release (Log D) - Mean -0.8081 Smoke Release (Log D) - Standard Error 0.1513 No of samples which did not ignite 1

For Samples which did not ignite

Smoke Release (Log D) - Mean -1 4544 Smoke Release (Log D) - Standard Error 0.0000 Number of specimens tested:

136163 28985 Page 1 of 2

Australian Wool testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing

Mechanical Testing

Performance & Approvals Testing

: Accreditation No Accreditation No

· Accreditation No.

983 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



A. JACKSON B.Sc.(Hons)

## **AWTA Product Testing**

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

## **TEST REPORT**

Client: Basford Brands Pty Ltd

> 16 - 20 Apparel Close Breakwater VIC 3219

18-003768 Test Number :

**Issue Date** 17/07/2018 17/07/2018 **Print Date** 

Regulatory Indices:

Ignitability Index Spread of Flame Index Heat Evolved Index

Smoke Developed Index

15 Range 0-20

0 Range 0-10

Range 0-10

Range 0-10

These results only apply to the specimen mounted, as described in this report. The result of this fire test may be used to directly assess fire hazard, but it should be recognised that a single test method will not provide a full assessment of fire hazard under all fire conditions.

The reaction of thin unsupported flexible materials to flame impingement can be assessed in accordance with AS 1530.2. Where materials of thickness less than 2mm that are sufficiently flexible to be bent by hand around a mandrel of 2mm diameter or less are subjected to the test described herein, they should also be subjected to the test in AS 1530.2.

The specimens melted and flowed away from the area of maximum heat during the test. Due to this phenomena it should be recognised that this test result may not be a true indication of the product's fire hazard properties.

To allow free movement of sample during testing all corners were folded away from the clamps.

Each test specimen was sandwiched between two layers of galvanised welded square mesh made from wire of nominal diameter 0.8mm and nominal spacing 12mm in both directions, stapled through at four points, each 100mm from the centre of the sample and the assembly clamped in four places.

136163 28985 Page 2 of 2

Australian Wool testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing

Mechanical Testing

Performance & Approvals Testing

: Accreditation No Accreditation No.

· Accreditation No.

1356

983

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



. JACKSON B.Sc.(Hons)

APPROVED SIGNATORY