

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106


1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Basford Brands Pty Ltd
16 - 20 Apparel Close
Breakwater VIC 3219

Test Number : 26-001419
Issue Date : 29/05/2026
Print Date : 29/05/2026

Sample Description Clients Ref : "Winton"
Woven curtaining fabric with backcoating
Colour : Natural
End Use : Curtains
Nominal Mass per Unit Area/Density : 342g/m2
Nominal Thickness : Approx 1mm



379105

83381

Page 1 of 3

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Fiona McDonald

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Basford Brands Pty Ltd
16 - 20 Apparel Close
Breakwater VIC 3219

Test Number : 26-001419
Issue Date : 29/05/2026
Print Date : 29/05/2026

AS/NZS 1530.3-1999

**Methods for Fire Tests on Building Materials, Components and Structures
Part 3: Simultaneous Determination of Ignitability,
Flame Propagation, Heat Release and Smoke Release**

Face tested: Face (Natural)

Date tested: 28-05-2026

	Standard Error	Mean
Ignition time	Nil	Nil min
Flame propagation time	Nil	Nil sec
Heat release integral	Nil	Nil kJ/m ²
Smoke release, log d	0.000	-0.8259
Optical density, d		0.1494 / metre

No of samples which ignited 2

For Samples which ignited

Smoke Release (Log D) - Mean -0.8259

Smoke Release (Log D) - Standard Error 0.0000

No of samples which did not ignite 7

For Samples which did not ignite

Smoke Release (Log D) - Mean -2.0235

Smoke Release (Log D) - Standard Error 0.0383

Number of specimens tested: 9

Regulatory Indices:

Ignitability Index 0 Range 0-20

Spread of Flame Index 0 Range 0-10

Heat Evolved Index 0 Range 0-10

Smoke Developed Index 5 Range 0-10

379105

83381

Page 2 of 3

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Basford Brands Pty Ltd
16 - 20 Apparel Close
Breakwater VIC 3219

Test Number : 26-001419
Issue Date : 29/05/2026
Print Date : 29/05/2026

Each test specimen was sandwiched between two layers of galvanised welded square mesh made from wire of nominal diameter 0.8mm and nominal spacing 12mm in both directions, stapled through at four points, each 100mm from the centre of the sample and the assembly clamped in four places.

To allow free movement of sample during testing all corners were folded away from the clamps.

The reaction of thin unsupported flexible materials to flame impingement can be assessed in accordance with AS 1530.2. Where materials of thickness less than 2mm that are sufficiently flexible to be bent by hand around a mandrel of 2mm diameter or less are subjected to the test described herein, they should also be subjected to the test in AS 1530.2.

Ignition is initiated by a pilot flame that is held near, but does not touch the specimen. A material that does not ignite during the standard test may ignite if contacted with a pilot flame during the test.

The specimens melted and flowed away from the area of maximum heat during the test. Due to this phenomena it should be recognised that this test result may not be a true indication of the product's fire hazard properties.

These results only apply to the specimen mounted, as described in this report. The result of this fire test may be used to directly assess fire hazard, but it should be recognised that a single test method will not provide a full assessment of fire hazard under all fire conditions.

379105

83381

Page 3 of 3

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



A handwritten signature in blue ink, appearing to read 'Fiona McDonald'.

Fiona McDonald

APPROVED SIGNATORY

A handwritten signature in black ink, appearing to read 'Michael A. Jackson'.

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR